

KLM100B(H)

Liquified Methylene diphenyl Di-Isocyanate (LMDI) Modified MDI



Karun Petrochemical Company

Address :

Head office:

No.17,Khalilzadeh St., Vali-e-asr
Ave., Vanak Sq., Tehran-Iran

Factory:

Site 2,Petrochemical Special
Economic Zone (Pet zone), Bandar-
e-Imam Khomeini, Iran.

☎ 0098 21 88786992-4

📠 0098 21 88677428

Web-site :

www.krnpc.ir

E-mail :

NDashti@krnpc.ir

Property	Specification	Analytical Method
Appearance	Yellow liquid	Visual
NCO Wt. %	28-30	ASTM D5155-14 Method A
Acidity as HCl Wt. %	Max. 0.01	ASTM 5629-11
Viscosity at 25(°C) mPa.s	Max. 100	ASTM D4889-15
Specific Gravity at 25(°C)	1.18-1.20	ASTM D4659-14

⇒ The current manufacturing technology of most isocyanates is based on the phosgenation of primary amines.

■ Application areas

KLM100B(H) is commonly used to manufacture:

- ✓ Shoe soles – used to produce prepolymers for shoe soles
- ✓ Adhesive – used to produce laminated adhesives in packaging industry
- ✓ Medical – used to produce orthopedic band
- ✓ Elastomers – used to produce films, linings, abrasive wheels and other mechanical items that require abrasion and solvent resistance
- ✓ Urethane sealants – used in construction applications
- ✓ Cast elastomers – for production of articles such as roller blade wheels
- ✓ Flexible foams – used to produce prepolymers for fabrication of bedding, furniture, automotive seating, flexible packaging and carpet underlay; this is the largest market application for MDI

■ Handling and storage conditions

Use only with adequate ventilation. Do not eat, drink, or smoke in working area. Never use welding/cutting torch near storage containers, even if empty, because even residual product can ignite explosively. Product must be stored at 20°C to 40°C.

Storage stability: The best time is 6 month since the date of production.

■ Packing details

In 220 lit (225 kg Net.) new steel drum, each 4 drums strapped on a wooden pallet.

■ Licensor: Chematur Engineering (CEAB), Sweden.