

**A mixture of Polyol-modified Monomeric MDI and Polymeric MDI
(MDI-Prepolymer)**



Karun Petrochemical Company

Address :

Head office:

No.17,Khalilzadeh St., Vali-e-asr
Ave., Vanak Sq., Tehran-Iran

Factory:

Site 2,Petrochemical Special
Economic Zone (Pet zone), Bandar-
e-Imam Khomeini, Iran.

☎ 0098 21 88786992-4

☎ 0098 21 88677428

Web-site :

www.krnpc.ir

E-mail :

NDashti@krnpc.ir

Property	Specification	Analytical Method
Appearance	Dark Brown liquid	Visual
NCO (Wt. %)	28-30	ASTM D5155-14 Method A
Acidity as HCl (Wt.%)	Max. 0.03	ASTM 5629-11
Viscosity at 25(°C) (mPa.s)	Max. 200	ASTM D4889-15
Specific Gravity at 25(°C)	1.18-1.20	ASTM D4659-14
Isocyanate Equivalent Weight (gr/eq)	140-150	ASTM D5155-14 Method A
Hydrolysable Chlorine (Wt.%)	Max. 0.1	ASTM D4663-15

⇒The current manufacturing technology of most isocyanates is based on the phosgenation of primary amines.

■ **Application areas**

KHR-45 is commonly used to manufacture high resilience (HR) molded foam which used to fabricate the automotive seating, furniture, flexible packaging and carpet underlay

■ **Handling and storage conditions**

Use only with adequate ventilation. Do not eat, drink, or smoke in working area. Never use welding/cutting torch near storage containers, even if empty, because even residual product can ignite explosively. Product must be stored at 20°C to 40°C.

Storage stability: The shelf life is 6 month since the date of production.

■ **Packing details**

In 220 lit (225 kg Net.) new steel drum, each 4 drums strapped on a wooden pallet.

■ **Licensor: Chematur Engineering (CEAB), Sweden.**